SPS-N/SPS-W Plastic Screw - Hex Nuts / Washers - PPS Selection CAD Heat-resistance Chemical-proof



SPS-N SPS-W

Material/Finish

RoHS Compliant SPS-N / SPS-W

Main body

PPS (Polyphenylene Sulfide) / Bright Light Brown Glass Fiber 40%

Heat Resistance Temperature*

*This is the value for the plastic material. The maximum operating temperature of the product changes with performance conditions such as tightening torque.

- PPS has excellent heat resistance and chemical resistance and continuous duty temperature of 200 deg C. Under 200 deg C, no oils, fats, or organic solvents dissolve PPS.
- It has high strength, high rigidity, and high heat resistance strength.
- It has high incombustibility that meets V-0 of UL 94.
- The properties and precautions of plastic screws → P.724

Application

FPD production equipment, semiconductor devices, printed circuit board etching devices, metallic surface treatment equipment and facilities, chemical plants, transformers, electrical and electronic equipment, hot water pumps, and chemical pumps

SPS-N Hex Nuts									
Part Number 1	M	В	T	Mass (g)	Qty per pack*1				
SPS-M2-N	M2	4	1.6	0.026	20				
SPS-M2.6-N	M2.6	5	2	0.05	20				
SPS-M3-N	M3	5.5	2.4	0.07	20				
SPS-M4-N	M4	7	3.2	0.17	20				
SPS-M5-N	M5	8	4	0.25	20				
SPS-M6-N	M6	10	5	0.52	10				
SPS-M8-N	M8	13	6.5	1.2	10				
SPS-M10-N	M10	17	8	2.4	5				
SPS-M12-N	M12	19	10	3.5	5				

*1 The minimum order quantity is 1 piece. → P.794

SPS-W Washers Unit: mm									
Part Number 1	d	D	t	Nominal	Mass (g)	Qty per pack*1			
SPS-3-W	3.2	7	0.5	3	0.025	20			
SPS-4-W	4.3	9	0.8	4	0.065	20			
SPS-5-W	5.3	10	1	5	0.094	20			
SPS-6-W	6.4	12.5	1.6	6	0.24	10			
SPS-8-W	8.4	17	1.6	8	0.46	10			
SPS-10-W	10.5	21	2	10	0.86	5			
SPS-12-W	13	24	2.5	12	1.3	5			

*1 The minimum order quantity is 1 piece. → P.794

• Part number specification



Order in number of packs. The minimum order quantity is 1 piece. → P.794

1 Individual Sales → P.794 🦸 Cleanroom Wash & Packaging → P.792 🞳 in Screw Length Adjustment → P.796 1 Vibration Resistant → P.795 1 Modification process for captive use → P.791 Available / Add'l charge | Available / Add'l charge Not Available Not Available Not Available